

TECHNICAL DATA SHEET

=====

ORIGINAL

CARBON BLACK N330	STANDARDS
IODINE ADSORPTION VALUE G/KG	82±7
DBP ABSORPTION VALUE 10 ⁻⁵ M ³ /KG	102±7
TINTING STRENGTH %	96-112
45μ m SIEVE RESIDUE %, ≤	0.100
150μ m SIEVE RESIDUE %, ≤	0.02
500μ m SIEVE RESIDUE %, ≤	0.0010
ASH CONTENT %, ≤	0.7
FINE CONTENT %, ≤	10
HEATING LOSS %, ≤	2.5
IMPURITY	NAUGHT
POUR DENSITY KG/M ³	380 ± 40
STRESS AT 300% ELONGATION (MPA)	-0.9 ±1.0