

IONIC YELLOW 10GA

Full Shade



Tinting Shade ($\text{TiO}_2 \times 10$)



Properties

Composition Lead Chromate-Lead Sulfate

Bulking value 160~200 (ml/100g)

Specific gravity 5.8 ± 0.3

Oil absorption 14~18 (ml/100g)

Matter soluble in water 1.0% max.

Moisture 1.0% max.

Residue on No.325 mesh sieve 0.5% max.

Fastness to

Light 2 (1~8)

Heat 4 (1~8)

Acid (2% H_2SO_4) 3 (1~5)

Alkali (1% NaOH) 2 (1~5)

NIC CORPORATION

[HEAD OFFICE]

Kitahama-Yamamoto Bldg. 7F 2-3-6 Kitahama,
Chuo-Ku, Osaka 541-0041, Japan

TEL 81-6-6232-2123

FAX 81-6-6232-0115

e-mail nic-ms@d8.dion.ne.jp

e-mail nic-ym@f4.dion.ne.jp

[TOKYO SALES OFFICE]

1-325 Miyahara-Cho, Kita-Ku,
Saitama-Shi, Saitama-Ken,
331-0812, Japan

TEL 81-48-662-6855

FAX 81-48-662-6866