

IONIC YELLOW G-EX

Full Shade



Tinting Shade ($\text{TiO}_2 \times 10$)



Properties

Composition	Lead Chromate-Lead Oxide
-------------------	--------------------------

Bulking value	250~300 (ml/100g)
---------------------	-------------------

Specific gravity	5.7 $\pm$ 0.3
------------------------	---------------

Oil absorption	20~26 (ml/100g)
----------------------	-----------------

Matter soluble in water	1.0% max.
-------------------------------	-----------

Moisture	1.0% max.
----------------	-----------

Residue on No.325 mesh sieve	0.5% max.
------------------------------------	-----------

Fastness to

Light	5 (1~8)
-------------	---------

Heat	5 (1~8)
------------	---------

Acid (2% H_2SO_4)	3 (1~5)
--	---------

Alkali (1% NaOH)	2 (1~5)
----------------------------------	---------



NIC CORPORATION

[HEAD OFFICE]

Kitahama-Yamamoto Bldg. 7F 2-3-6 Kitahama,
Chuo-Ku, Osaka 541-0041, Japan

TEL 81-6-6232-2123

FAX 81-6-6232-0115

e-mail nic-ms@d8.dion.ne.jp

e-mail nic-ym@f4.dion.ne.jp

[TOKYO SALES OFFICE]

1-325 Miyahara-Cho, Kita-Ku,
Saitama-Shi, Saitama-Ken,
331-0812, Japan

TEL 81-48-662-6855

FAX 81-48-662-6866