



# IONIC YELLOW 7000

Full Shade



Tinting Shade (TiO<sub>2</sub> x 10)



## Properties

|                                                 |                                       |
|-------------------------------------------------|---------------------------------------|
| Composition .....                               | Lead Chromate-Lead Sulfate and Silica |
| Bulking value .....                             | 250~300 (ml/100g)                     |
| Specific gravity .....                          | 4.3 ± 0.3                             |
| Oil absorption .....                            | 27~33 (ml/100g)                       |
| Matter soluble in water .....                   | 1.0% max.                             |
| Moisture .....                                  | 1.0% max.                             |
| Residue on No.325 mesh sieve .....              | 0.5% max.                             |
| Fastness to                                     |                                       |
| Light .....                                     | 7 (1~8)                               |
| Heat .....                                      | 8 (1~8)                               |
| Acid (2% H <sub>2</sub> SO <sub>4</sub> ) ..... | 5 (1~5)                               |
| Alkali (1% NaOH) .....                          | 5 (1~5)                               |

## NIC CORPORATION

### [HEAD OFFICE]

Kitahama-Yamamoto Bldg. 7F 2-3-6 Kitahama,  
Chuo-Ku, Osaka 541-0041, Japan  
TEL 81-6-6232-2123  
FAX 81-6-6232-0115  
e-mail nic-ms@d8.dion.ne.jp  
e-mail nic-ym@f4.dion.ne.jp

### [TOKYO SALES OFFICE]

1-325 Miyahara-Cho, Kita-Ku,  
Saitama-Shi, Saitama-Ken,  
331-0812, Japan  
TEL 81-48-662-6855  
FAX 81-48-662-6866