

## Silwet® 408

### Silwet® 408

#### Description


Silwet 408 spray adjuvant is a superspreading surfactant based on a trisiloxane ethoxylate. Silwet 408 spray adjuvant lowers the surface tension of spray solutions, beyond that which is achievable with conventional adjuvants.

Typically, Silwet 408 spray adjuvant (@ 0.1 wt %) gives an aqueous surface tension of <22 mN/m. On the other hand, an octylphenol ethoxylate containing 10 EO units (a commonly used nonionic surfactant) at 1.0 wt % gives a surface tension of only 30 mN/m.

The bottom line? Silwet 408 spray adjuvant helps lower the aqueous surface tension more effectively than conventional spray adjuvants.


Because Silwet 408 spray adjuvant is a superspreading surfactant, the contact angle of spray solutions on leaf surfaces is reduced, leading to an increase in spray coverage (Figure 1).

Figure 1: Spreading




Additionally, under specific conditions, Silwet 408 spray adjuvant promotes rapid uptake of agrochemicals into plants via stomatal infiltration. Spray solutions taken into plants in this way become rainfast, thereby improving application reliability (Figure 2).

Figure 2: Uptake



Unlike other trisiloxane alkoxylates, which are negatively affected by oil based components (i.e. EC formulations, spray oils, etc.), Silwet 408 spray adjuvant provides enhanced spreading in many of these types of formulations relative to competitive organosilicone based adjuvants (Figure 3).

**Figure 3: Spreading of Oil Based Agrochemicals (EC Formulation)**



Silwet 408 spray adjuvant is nonionic in nature, making it useful with a broad range of agrochemical formulations.

### Key Features and Benefits

- Superspread for soluble liquid and emulsifiable concentrate formulations
- Promotes spray volume reduction
- Promotes rapid uptake of agrochemicals (rainfastness)
- Improves spray coverage
- Nonionic
- Meets requirements of EPA 40CFR§180.910

### Typical Physical Properties

Property	Result
Surface Tension (0.1%, mN/m) <sup>(a)</sup>	21.5
Cloud Point (0.1 wt%), °C	<10
Viscosity (cSt @ 25°C)	35
CMC (Wt%) <sup>(b)</sup>	0.007
Pour Point, °C	-8
Specific Gravity (25/25°C)	1.020

Flash Point<sup>(c)</sup> °C

118

- (a) Surface Tension by Wilhelmy Plate Method
- (b) Critical Micelle Concentration
- (c) Pensky-Martens Closed Cup, ASTM Method D93

## Potential Applications

Silwet 408 spray adjuvant has been used successfully in spray applications globally.

Typical applications include:

Application	Typical Use Rate <sup>(a)</sup>
Plant Growth Regulators	0.025% to 0.05%
Herbicide	0.025% to 0.15%
Insecticide	0.025% to 0.1%
Fungicide	0.015% to 0.05%
Fertilizers and Micronutrients	0.015% to 0.1%

(a) Note: use rates are dependent on crop, agrochemical and spray volume requirements.

## Product Usage

### In Agrochemical Formulations

Silwet 408 spray adjuvant may be used as a component in agrochemical formulations. Although organosilicone surfactants are subject to hydrolysis under acidic or basic conditions, optimum performance is achieved by buffering the formulation to pH 6.5 - 7.5. Additionally, it is recommended that Silwet 408 spray adjuvant be used at a concentration of at least 5%, based on the total formulation.

### As A Tank Mix Adjuvant

Silwet 408 spray adjuvant, when used as a tank-side adjuvant may be used to improve spray coverage, improve uptake or to allow for a reduction in spray volume. Silwet 408 spray adjuvant is most effective as a tank-side adjuvant when spray mixtures are 1) within a pH range of 5-8, and 2) used within 24 hours of preparation.

High spray volumes, coupled with high surfactant rates, are not required to achieve sufficient coverage with Silwet 408 spray adjuvant. In fact, Silwet 408 spray adjuvant has the potential to provide adequate coverage in many low volume spray applications

at rates between 0.025% and 0.1%.

#### **Patent Status**

Standard copy to come

#### **Product Safety, Handling and Storage**

Standard copy to come

#### **Limitations**

Standard copy to come

#### **Contact Information**

For product prices, availability, or order placement, contact our customer service at  
[Momentive.com/CustomerService/](http://Momentive.com/CustomerService/)

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

#### **DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS**

**OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*Silwet is a trademark of Momentive Performance Materials Inc.

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**